

TECHNICAL SPECIFICATION: SPOOLED COIL ALFA 500 KSD



Description of the product

Weldable, sustainable reinforcing steel featuring improved bonding and high ductility, hot rolled with in-line heat treatment "Tempcore".

Range of dimensions

- Diameter: 8 – 16 mm

Packaging

Spoiled coils fastened in 4 points

Weight of each spoiled coil:

- ~ 3000 kg

Coil size:

- $\varnothing$ int. 700 mm
- $\varnothing$ ext. 1100 ÷ 1200 mm
- Height 700 mm

Labelling

Each spoiled coil is identified with a metal or paper plastic label containing the following information:

- Company logo
- Heat number
- Diameter
- Weight
- Steel grade
- Production date
- Standards references
- Certification logos
- QR Code

TECHNICAL SPECIFICATION: SPOOLED COIL ALFA 500 KSD

Certifications

Each delivery is accompanied by the certificate 3.1 (standard UNI EN 10204)

RIBS GEOMETRY AND ROLLING MARKING



CONFORMITY TO STANDARDS

Country (trade name)	Standard	Grade	Certifications
GREECE	ELOT 1421-3	B 500 C	✓
GERMANY	DIN 488	B 500 B	✓
CROATIA	HRN 1130-2	B 500 B	✓
BULGARIA	BDS 9252:2007	B500B - B500C	✓

CHEMICAL COMPOSITION

C % max	P % max	S % max	Cu % max	N % max	Ceq. Max
0.22	0.050	0.050	0.80	0.012	0.50
(0.24)	(0.055)	(0.055)	(0.85)	(0.014)	(0.52)

The figures in brackets refer to product analysis

MECHANICAL PROPERTIES

Standard	Grade	Re N/mm ²	Rm N/mm ²	Rm/Re	Agt %	A5 %	A10 %
ELOT 1421-3	B 500 C	≥ 500		≥ 1.15 ≤ 1.35	≥ 7.5		
D.M. 17/01/2018	B450 C	≥ 450	≥ 540	≥ 1.15 ≤ 1.35	≥ 7.5		
DIN 488	B 500 B	≥ 500		≥ 1.08	≥ 5		
HRN 1130-2	B 500 B	≥ 500		≥ 1.08	≥ 5		
BDS 9252:2007	B500B - B500C	≥ 500		≥ 1.15 ≤ 1.35	≥ 7.5		

TECHNICAL SPECIFICATION: SPOOLED COIL ALFA 500 KSD

GEOMETRICAL CHARACTERISTICS				
$\varnothing$ mm	8	10	12	≥ 14
Relative rib area fR	≥ 0.040	≥ 0.040	≥ 0.040	≥ 0.056
Relative rib area fR DIN 488	≥ 0.045	≥ 0.052	≥ 0.056	≥ 0.056